GENERAL SPECIFICATIONS

RESILIENCE

The faux leather that builds luxury into performance

P

This is an up-to-date spec sheet. This pattern never contained flame retardant, anti-bacterial, or anti-microbial additives.

## Notion

SURFACE COMPOSITION SUBSTRATE COMPOSITION WEIGHT WIDTH THICKNESS	100% PVC (Phthalate Free) 100% Polyester 31 oz per linear yard 54" 1.20 mm	
ADDED PERFORMANCE SPECIFICATIONS STAIN RESISTANCE COLORFASTNESS TO LIGHT BLEACH RESISTANCE COLD CRACK DENIM DYE TRANSFER RESISTANCE SULFIDE STAIN RESISTANCE	Yes 300 Hours Yes, 10% Dilution -20° F Yes Yes	AATCC 16.3-2014, Option 3 CFFA-6a-2007
PHYSICAL PERFORMANCE SPECIFICATIONS ABRASION RESISTANCE BREAKING STRENGTH COATING ADHESION	250,000+ Double Rubs* 95 Warp, 73 Fill 8.0 Warp, 8.1 Fill	ASTM D4157-13 ASTM D751-06 ASTM D751-06

CROCKING RESISTANCE	5 Dry, 5 Wet	AATCC 8-2016
FLEX RESISTANCE	25,000+	ASTM D2097-0
TEAR STRENGTH: TONGUE TEAR	7.2 Warp, 11.0 Fill	ASTM D751-06
SEAM STRENGTH: TACK TEAR	48.8 Warp, 40.0 Fill	ASTM D751-06
*Abrasion test results exceeding ACT Performance Guidelines are not an	indicator of product lifespan.	

FLAME RETARDANCY SPECIFICATIONS	

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass
FMVSS 302	Pass

## **REDUCED ENVIRONMENTAL IMPACT**

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS PHTHALATE FREE LEAD / HEAVY METAL FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS





<sup>\*</sup>ACT® Registered Certification Marks

D2097-03 D751-06 D751-06