RESILIENCE

The faux leather that builds luxury into performance

Ð

This spec sheet has been updated to reflect the removal of flame retardant, anti-bacterial, and anti-microbial additives.

## Phoenix

GENERAL SPECIFICATIONS SURFACE COMPOSITION SUBSTRATE COMPOSITION WEIGHT WIDTH	100% PVC (Phthalate Free) 100% Polyester 28 oz per linear yard 54"	
THICKNESS	1.00 mm	
ADDED PERFORMANCE SPECIFICATIONS STAIN RESISTANCE COLORFASTNESS TO LIGHT BLEACH RESISTANCE COLD CRACK SULFIDE STAIN RESISTANCE	Yes 650 Hours Yes, 10% Dilution -20° F Yes	AATCC 16.3-2014, Option 3 CFFA-6a-2007
PHYSICAL PERFORMANCE SPECIFICATIONS ABRASION RESISTANCE BREAKING STRENGTH COATING ADHESION CROCKING RESISTANCE FLEX RESISTANCE TEAR STRENGTH: TONGUE TEAR SEAM STRENGTH: TACK TEAR	150,000+ Double Rubs* 86 Warp, 62 Fill 7.4 Warp, 7.5 Fill 5 Dry, 5 Wet 25,000+ 5.1 Warp, 6.9 Fill 41 Warp, 32 Fill	ASTM D4157-13 ASTM D751-06 ASTM D751-06 AATCC 8-2013 ASTM D2097-03 ASTM D751-06 ASTM D751-06

\*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

## FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass
FMVSS 302	Pass

## REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS PHTHALATE FREE LEAD / HEAVY METAL FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS





\*ACT® Registered Certification Marks