RESILIENCE

The faux leather that builds luxury into performance

Þ

This spec sheet has been updated to reflect the removal of flame retardant, anti-bacterial, and anti-microbial additives.

3

Seduction

GENERAL SPECIFICATIONS SURFACE COMPOSITION SUBSTRATE COMPOSITION WEIGHT WIDTH THICKNESS	100% PVC (Phthalate Free) 100% Polyester 32 oz per linear yard 54" 1.05 mm	
ADDED PERFORMANCE SPECIFICATIONS		
STAIN RESISTANCE COLORFASTNESS TO LIGHT	Yes 500 Hours	AATCC 16 3-2012/ Option 3
BLEACH RESISTANCE	Yes, 10% Dilution	AATCC 16.3-2012/, Option 3
COLD CRACK	-20° F	CFFA-6a-2007
SULFIDE STAIN RESISTANCE	Yes	
PHYSICAL PERFORMANCE SPECIFICATIONS		
ABRASION RESISTANCE	500,000+ Double Rubs*	ASTM D4157-10
BREAKING STRENGTH	128 Warp, 93 Fill	ASTM D751-06
COATING ADHESION	4.3 Warp, 3.9 Fill	ASTM D751-06
CROCKING RESISTANCE	5 Dry, 5 Wet	AATCC 8-2007
FLEX RESISTANCE	25,000+	ASTM D2097-03
TEAR STRENGTH: TONGUE TEAR	7.7 Warp, 6.8 Fill	ASTM D2261-07
SEAM STRENGTH: TACK TEAR	51 Warp, 37.8 Fill	ASTM D751-06

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass
FMVSS 302	Pass

REDUCED ENVIRONMTENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS PHTHALATE FREE LEAD / HEAVY METAL FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS





^{*}ACT® Registered Certification Marks