

Thompson

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD) 19 oz per linear yard

WIDTH

COMPOSITION 100% Polyester

■ PIECE DYED ☐ YARN DYED ☐ FIBER DYED

□ DOBBY □ JACQUARD ■ PILE

YARN PER INCH 76.2 EPI, 48.3 PPI

YARN SIZE 300-450DN Warp, 300-450DN Fill

BACKING None STAIN RESISTANCE C6

CLEANING CODE S, Spot clean using water-free solvent or dry cleaning product. Cleaning

54"

by a professional service is recommended.

PHYSICAL PERFORMANCE SPECIFICATIONS

 ABRASION RESISTANCE
 100,000+ Double Rubs*
 ASTM D4157-13

 BREAKING STRENGTH
 309 Warp, 130 Fill
 ASTM D5034-09

 BRUSH PILL
 Class 5
 ASTM D3511

 CROCKING RESISTANCE
 4.5 Dry, 4.5 Wet
 AATCC 8-2007

COLORFASTNESS TO LIGHT Class 4.5 AATCC 16.3-2012, Option 3

SEAM SLIPPAGE 134.4 Warp, 120.8 Fill ASTM D4034-92

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13 Pass
UFAC CLASS I Pass
NFPA 260 Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65
NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT
NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS
LEAD / HEAVY METAL FREE
BPA FREE / TRIS FREE / FORMALDEHYDE FREE
DOES NOT CONTAIN CONFLICT MINERALS









*ACT® Registered Certification Marks