Verve II

This is an up-to-date spec sheet. This pattern never contained flame retardant, anti-microbial, or anti-bacterial additives.

CFFA-6a-2007

GENERAL SPECIFICATIONS

SURFACE COMPOSITION100% PolyurethaneSUBSTRATE COMPOSITION100% PolyesterWEIGHT16.5 oz per linear yard

 WIDTH
 54"

 THICKNESS
 0.85 mm

Z

ADDED PERFORMANCE SPECIFICATIONS

HYDROLYSIS RESISTANCE 5 Weeks ISO 1419:1995 (Jungle Test)

STAIN RESISTANCE Yes

COLORFASTNESS TO LIGHT 300 Hours AATCC 16.3-2014, Option 3

BLEACH RESISTANCE Yes, 10% Dilution AATCC 107-13, Modified

COLD CRACK -20° F

SULFIDE STAIN RESISTANCE Yes

PHYSICAL PERFORMANCE SPECIFICATIONS

ABRASION RESISTANCE 250.000+ Double Rubs* ASTM D4157-13 **BREAKING STRENGTH** 143 Warp, 105 Fill ASTM D751-06 **COATING ADHESION** 10.2 Warp, 9.1 Fill ASTM D751-06 **CROCKING RESISTANCE** 5 Dry, 5 Wet **AATCC 8-2013 FLEX RESISTANCE** 25.000+ ASTM D2097-03 **TEAR STRENGTH: TONGUE TEAR** 7.4 Warp, 12.7 Fill ASTM D751-06 **SEAM STRENGTH: TACK TEAR** 55.9 Warp, 44.9 Fill ASTM D751-06

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13 Pass
UFAC CLASS I Pass
NFPA 260 Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65
NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT
NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS
PHTHALATE FREE
LEAD / HEAVY METAL FREE
BPA FREE / TRIS FREE / FORMALDEHYDE FREE
DOES NOT CONTAIN CONFLICT MINERALS





*ACT® Registered Certification Marks