This spec has been updated to reflect the removal of flame retardant additives.

Vintage

GENERAL SPECIFICATIONS

SURFACE COMPOSITION100% PVC (Phthalate Free)SUBSTRATE COMPOSITION75% Polyester/25% CottonWEIGHT36 oz per linear yard

WIDTH 54"
THICKNESS 1.10 mm

ADDED PERFORMANCE SPECIFICATIONS

COLORFASTNESS TO LIGHT 300 Hours AATCC 16.3-2014, Option 3

BLEACH RESISTANCE Yes, 10% Dilution

COLD CRACK -20° F CFFA-6a-2007

SULFIDE STAIN RESISTANCE Yes

PHYSICAL PERFORMANCE SPECIFICATIONS

ABRASION RESISTANCE 50.000+ Double Rubs* ASTM D4157-13 **BREAKING STRENGTH** 67 Warp, 83 Fill ASTM D751-06 **COATING ADHESION** 9.6 Warp, 9.9 Fill ASTM D751-06 **CROCKING RESISTANCE** 4.5 Dry, 4 Wet **AATCC 8-2013 FLEX RESISTANCE** 25.000+ ASTM D2097-03 **TEAR STRENGTH: TONGUE TEAR** 5.6 Warp, 6.2 Fill ASTM D751-06 **SEAM STRENGTH: TACK TEAR** 68 Warp, 65 Fill ASTM D751-06

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13 Pass
UFAC CLASS I Pass
NFPA 260 Pass
FMVSS 302 Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65
NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT
NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS
PHTHALATE FREE
LEAD / HEAVY METAL FREE
BPA FREE / TRIS FREE / FORMALDEHYDE FREE
DOES NOT CONTAIN CONFLICT MINERALS





*ACT® Registered Certification Marks