Huron

GENERAL SPECIFICATIONS WEIGHT (LINEAR YARD) WIDTH COMPOSITION

□ PIFCF DYFD DOBBY

☐ YARN DYFD □ JACQUARD

YARN PER INCH YARN SIZE BACKING MINIMUM YARDAGE CUSTOM COLOR CLEANING CODE

PHYSICAL PERFORMANCE SPECIFICATIONS

100.000+ Double Rubs* ABRASION RESISTANCE HYDROSTATIC PRESSURE (SUTER) BREAKING STRENGTH **BRUSH PILL** Class 4 CROCKING RESISTANCE COLORFASTNESS TO LIGHT SEAM SLIPPAGE WATER REPELLENCY SPRAY TEST 100 TEAR STRENGTH: TONGUE TEAR **BLEACH RESISTANCE** *Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS LEAD / HEAVY METAL EREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS



Disclaimer: This product meets the Healthy Interior goals of the Safer Chemical Challenge according to the manufacturer Practice Greenhealth does not verify this information.

17 oz per linear yard 54" 91% Polyester / 7% Polyurethane / 2% Silicone

■ FIBER DYED D PILE

29.7 EPI, 26.6 PPI 1250D Warp. 1250D Fill Polvurethane 500 Yards

SW, Spot clean with upholstery shampoo, foam from a mild detergent, or a mild dry cleaning solvent. Do not saturate with liquid. Pile fabrics may require brushing to restore appearance. Cushion cover should not be removed and dry cleaned.

BC, Lightly spray with a 10% dilution of Household Bleach and water. After the appropriate contact time, blot surface dry and wipe or rinse with fresh water and blot dry.

270+cm (maximum) 225 Warp, 195 Fill 4.5 Dry, 5 Wet Class 5, 40 hours 88.5 Warp, 89.5 Fill 46 Warp, 44.4 Fill Yes, 10% Dilution

ASTM D4157-13 AATCC 127-13, Option 1 ASTM D5034-09 ASTM D3511 AATCC 8-2016 AATCC 16.3-2014 ASTM D4034-92 AATCC 22-2014 ASTM D2261-13



*ACT® Registered Certification Marks