

Lucerne

GENERAL SPECIFICATIONS

WEIGHT (LINEAR YARD)

WIDTH

COMPOSITION

☐ PIFCF DYFD

DOBBY

YARN PER INCH YARN SIZE

BACKING

CLEANING CODE

18.05 oz per linear yard

54"

93% Polyester / 4% Polyurethane / 3% Silicone

FIBER DYFD

☐ PILE

83.3 EPI, 45.7 PPI

1250D+300DD Warp, 1250D Fill

Polyurethane

SW, Spot clean with upholstery shampoo, foam from a mild detergent, or a mild dry cleaning solvent. Do not saturate with liquid. Pile fabrics may require brushing to restore appearance. Cushion cover should not be removed and dry cleaned.

BC, Lightly spray with a 10% dilution of Household Bleach and water. After the appropriate contact time, blot surface dry and wipe or rinse with fresh water and blot dry.

PHYSICAL PERFORMANCE SPECIFICATIONS

ABRASION RESISTANCE HYDROSTATIC PRESSURE (SUTER) **BREAKING STRENGTH BRUSH PILL** CROCKING RESISTANCE COLORFASTNESS TO LIGHT

SEAM SLIPPAGE TEAR STRENGTH: TONGUE TEAR

BLEACH RESISTANCE

100,000+ Double Rubs* 270+cm (maximum) 290 Warp, 192 Fill Class 5 5 Dry, 5 Wet Class 5, 40 hours 93.5 Warp, 103.5 Fill

53 Warp, 22.7 Fill

Yes, 10% Dilution

AATCC 16.3-2014 ASTM D4034-92

ASTM D4157-13

ASTM D5034-09

ASTM D3511

AATCC 8-2016

AATCC 127-13, Option 1

ASTM D2261-13

*Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.

☐ YARN DYFD

☐ JACQUARD

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13 Pass **UFAC CLASS I** Pass **NFPA 260** Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS LEAD / HEAVY METAL FREE BPA FREE / TRIS FREE / FORMALDEHYDE FREE DOES NOT CONTAIN CONFLICT MINERALS









Disclaimer: This product meets the Healthy Interior goals of the Safer Chemical Challenge according to the manufacturer Practice Greenhealth does not verify this information.

