

Aspire

GENERAL SPECIFICATIONS

SURFACE COMPOSITION	100% PVC (Phthalate Free)
SUBSTRATE COMPOSITION	100% Polyester
WEIGHT	32 oz per linear yard
WIDTH	54"
THICKNESS	1.20 mm
COUNTRY OF ORIGIN	Turkey

ADDED PERFORMANCE SPECIFICATIONS

STAIN RESISTANCE	Yes	
COLORFASTNESS TO LIGHT	300 Hours	AATCC 16.3-2004, Option 3
BLEACH RESISTANCE	Yes, 10% Dilution	
COLD CRACK	-20° F	CFFA-6a-2007
SULFIDE STAIN RESISTANCE	Yes	

PHYSICAL PERFORMANCE SPECIFICATIONS

ABRASION RESISTANCE	250,000+ Double Rubs	ASTM D4157-10
BREAKING STRENGTH	175 Warp, 163 Fill	ASTM D751-06
COATING ADHESION	7.35 Warp, 6.13 Fill	ASTM D751-06
CROCKING RESISTANCE	5 Dry, 5 Wet	AATCC 8-2007
FLEX RESISTANCE	25,000+	ASTM D2097-03
TEAR STRENGTH: TONGUE TEAR	11.2 Warp, 18.9 Fill	ASTM D2261-07
SEAM STRENGTH: TACK TEAR	60.7 Warp, 79.1 Fill	ASTM D751-06
ELONGATION	87.2% Warp, 76.8% Fill	ASTM D751-06
STRETCH AND SET	Warp Stretch 22%, Set 3.10% Fill Stretch 22.11 %, Set 3.63% Bias Stretch 20%, Set 2.94%	SAE J855-2022

**Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.*

FLAME RETARDANCY SPECIFICATIONS

CALIFORNIA TECHNICAL BULLETIN 117:13	Pass
UFAC CLASS I	Pass
NFPA 260	Pass
FMVSS 302	Pass

REDUCED ENVIRONMENTAL IMPACT

THIS PRODUCT DOES NOT POSE ANY EXPOSURE RISKS ASSOCIATED WITH THE CHEMICALS IN PROP 65
 NO ADDED FLAME RETARDANT CHEMICALS - AB2998 COMPLIANT
 NO ADDED ANTI-BACTERIAL / ANTI-MICROBIAL CHEMICALS
 PHTHALATE FREE
 LEAD / HEAVY METAL FREE
 BPA FREE / TRIS FREE / FORMALDEHYDE FREE
 DOES NOT CONTAIN CONFLICT MINERALS



*ACT® Registered Certification Marks